

PORON® 4790-92-25031-04P-Extra Soft Slow-Rebound-Supported – Data Sheet

PROPERTY	TEST METHOD	VALUE
PHYSICAL		
Density, kg/m ³ (lb./ft ³)	ASTM D3574-95 Test A	400 (25)
Tolerance, %		± 10
Thickness, mm (inches)		0.79 (0.031)
Tolerance, %		± 15
Standard Color (Code)		Black (04)
Compression Force Deflection, Range kPa (psi), Typical kPa (psi)	0.51 cm/min (0.2" / min) Strain Rate Force Measured @ 25% Deflection	8 - 58 (1.25 - 8.5) 37 (5.3)
Compression Set, % max.	ASTM D 3574-95 Test D @ 23°C (73°F) ASTM D 3574-95 Test D @ 70°C (158°F)	2 10
ELECTRICAL AND THERMAL		
Dielectric Constant, K', "DK"	ASTM D 150 measurements at 22°C (72°F) relative humidity 50% for 24 hrs.	1.48
Dielectric Strength, volts/mil	ASTM D 149-97a	50
Dissipation Factor, tan D, "DF"	ASTM D 150-98	0.04
Volume Resistivity, ohm-cm	ASTM D 257-99	8.0 x 10 ¹¹
Surface Resistivity, ohm/sq.	ASTM D 257-99	10.0 x 10 ¹¹
Coefficient of Thermal Expansion		2.3 - 3.1 x 10 ⁻⁴ in./in./°C (1.3-1.7x10 ⁻⁴ in./in./°F)
TEMPERATURE RESISTANCE		
Recommended Constant Use, max.	SAE J-2236	90°C (194°F)
Recommended Intermittent Use, max.		121°C (250°F)
Embrittlement	ASTM D 746-98	-12°C (10°F)

The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers PORON Polyurethane Foam Materials for each application. The Rogers logo, Helping power, protect, connect our world and PORON are trademarks of Rogers Corporation or one of its subsidiaries. © 2003, 2004, 2008, 2009, 2018, 2020 Rogers Corporation, All rights reserved. Printed in U.S.A. 0620-PDF, Publication #17-086

Helping power, protect, connect our world™