

PORON® AquaPro® Family Formulation 37

PROPERTY	TEST METHOD	VALUE
PHYSICAL		
Density, kg/m ³ (lb./ft ³)	ASTM D 3574-95, Test A	224 (14)
Tolerance, kg/m ³ (lb./ft ³)		± 32 (2)
Thickness, mm (inches)	ASTM D 3574-95, Test A	1.5 - 12.7 (0.059 - 0.500)
Tolerance, %		± 10
Standard Color (Code)		Black (04)
Compression Force Deflection, kPa (psi)	0.51 cm/min (0.2"/min) Strain Rate Force Measured @ 25% Deflection	24 - 59 (3.5 - 8.5)
Compression Set, % max After 24 Hour Recovery	ASTM D3574-95 Test D @ 70°C (158°F)	10
Tensile Strength, min. kPa (psi)	ASTM D3574 Test E	248 (36)
Tensile Elongation, % min.	ASTM D3574 Test E	150
Tear Strength, min. kN/m, (pli)	ASTM D264 Die C	0.96 (5.5)
TEMPERATURE RESISTANCE		
Recommended Constant Use, max.	SAE J-2236	90°C (194°F)
Recommended Intermittent Use, max.	UL 157	121°C (250°F)
Embrittlement	ASTM D746	-42°C (-44°F)
Cold Flexibility	GMW3154 (Conical Mandrel Bend Test)	No Cracking



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of PORON Polyurethane Foam Materials for each application. The Rogers logo, PORON, and the PORON logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2015-2017, 2020, 2023 Rogers Corporation. All rights reserved. 0223-PDF • Publication #17-295 www.rogerscorp.com

PROPERTY	TEST METHOD	VALUE
FLAMMABILITY & OUTGASSING		
Flammability, mm (inches)	UL 94HBF [‡] (Pass ≥)	3.0 (0.118)
	FMVSS 302 (Pass ≥)	3.0 (0.118)
	GMW3232 (Pass ≥)	3.0 (0.118)
Fogging	SAE J-1756 3 hrs @ 100°C (212°F)	No Fogging
Outgassing, Total Mass Loss (TML) %	ASTM E595 24 hrs @ 125°C (257°F) @ <7 x 10 ³ Pa	0.81
Outgassing, Collected Volatile Condensable Materials (CVCM) %		0.02
Outgassing, Water Vapor Regain (WVR) %		0.49
ENVIRONMENTAL		
Gasketing and Sealing	UL JMST2 (Consisting of UL50 & UL508) CAN/CSA-C22.2 No. 94-M91	File MH15464
Moisture Absorption, High Humidity Exposure, % Weight Gain	AMS 3568	1.1
Water Absorption, Vacuum Exposure, % Weight Gain	ASTM D1056	5
UV Resistance, ΔE % Gloss Change	ASTM G154/SAE J1545	2.8 - 63
Ozone Resistance	ISO 1431-1	No cracks or other indication of material breakdown.
Corrosion Resistance	AMS 3568	6
Mildew Resistance	GMW 3259	No visual evidence of growth. No odor.

Notes:

[‡]Designed to meet UL 94 HBF based upon 2022 test criteria. As of 2023 items with spec range ≥ 15.6 lb/ft³ (250kg/m³) are no longer eligible to be tested for UL 94 HBF but remain equivalent.

- All metric conversions are approximate.
- Additional technical information is available.
- Typical values should not be used for specification limits.

To order PORON materials, please contact our Sales Specialists at 860.928.3622 or via email at EMS_CT_cust_serv@rogerscorporation.com



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of PORON Polyurethane Foam Materials for each application. The Rogers logo, PORON, and the PORON logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2015-2017, 2020, 2023 Rogers Corporation. All rights reserved. 0223-PDF • Publication #17-295 www.rogerscorp.com