

BISCO® BF-2000

BISCO® BF-2000 is a highly compressible, ultra soft silicone foam. The combination of low weight and softness makes it an ideal choice where low closure force and sealing are critical. The patented chemistry and cell structure provide a long term performance advantage.

Features & Benefits, applicable to all BISCO® Cellular Materials (Foams):

- Temperature independency
- UV/ Ozone resistant
- Rated to most stringent flame standards

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
PHYSICAL			
Color	Visual	Black	---
Thickness, mm (inches)	Internal	3.18 - 12.70 (0.125 - 0.500)	---
Density, kg/m ³ (lb./ft ³)	Internal	175 (11)	160 - 240 (9.98 - 14.98)
Compression Force Deflection, kPa (psi)	ASTM D1056	10 (1.5)	0 - 17 (0 - 2.5)
Compression Set, %	ASTM D1056 100°C (212°F) / 22 hrs / 50%	6.9	< 12
Water Absorption, %	Internal 2" below water surface / 24 hrs / change in weight	1.4	---

Specification values in bold are tested on a batch basis.

Further industry specifications tested in tables below.

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
FLAMMABILITY			
Flame Resistance	UL 94 (File E83967)	Meets	V-0 ; HF-1
Flame Spread Index (Is)	ASTM E162	Meets	Flaming Mode < 35
Smoke Density (Ds)	ASTM E662	Meets	Flaming Mode, 1.5 min, < 100 Flaming Mode, 4.0 min, < 200
Burn Length	FMVSS 302	Meets	< 100 mm/min

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
THERMAL			
Temperature Range, °C (°F)	Internal	-55 to +200 (-67 to +392)	---
Thermal Conductivity, W/m °K	ASTM C518	0.048	---
Low Temperature Flex	ASTM D1056 -55°C (-67°F) / 5 hrs	Pass	---
Low Temperature Brittleness	ASTM D746 -55°C (-67°F) / 3 min	Pass	---

Standard Thickness Tolerances

NOMINAL THICKNESS	TOLERANCE
mm (inches)	mm (inches)
3.18 (0.125)	± 0.762 (± 0.030)
4.78 (0.188)	± 0.762 (± 0.030)
6.35 (0.250)	± 1.016 (± 0.040)
9.53 (0.375)	± 1.524 (± 0.060)
12.70 (0.500)	± 1.524 (± 0.060)

Slit Material and Tape (PSA) Width Tolerances

NOMINAL WIDTH	TOLERANCE
mm (inches)	mm (inches)
> 0 - 76 (> 0 - 3)	± 1.60 (± 0.063)
> 76 - 203 (> 3 - 8)	± 2.39 (± 0.094)
> 203 - 305 (> 8 - 12)	± 3.18 (± 0.125)
> 305 - 457 (> 12 - 18)	± 4.78 (± 0.188)
> 457 - 660 (> 18 - 26)	± 5.56 (± 0.219)
> 660 - 914 (> 26 - 36)	+ 25.4/- 0 (+ 1/- 0)

VALUE ADDED OFFERINGS

- Adhesive (PSA) lamination
- Slit material/tapes

Notes:

*Typical Value- Value is based on historical data. Please note the frequency of testing varies.

**Specification- Applies to physical properties only, which are based on Rogers' internal benchmark and standard BISCO specification values. Additional industry specifications are available as well. All other properties are based on industry standard guidelines.

For more information and to request a sample, please contact our team of experts at solutions@rogerscorp.com



EKO-TECH Sp z o.o. sp. k.
ul. Fabryczna 1B, 42-660 Kalety
tel: 34 3578 624, e-mail: info@eko-tech.biz
www.eko-tech.biz | www.converting-tasm.pl



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO products for each application. The Rogers logo, BISCO, and the BISCO logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2003, 2006, 2009, 2017, 2019-2021, 2023 Rogers Corporation. All rights reserved. 1223-PDF • Publication #180-049