

tesa® 63608

Product Information



800µm double sided PE foam tape

Product Description

tesa® 63608 is a double sided PE foam tape for mounting applications.

Product Features

- High ultimate adhesion level for a reliable bonding performance
- Fully outdoor suitable: UV, water and ageing resistant
- Conformable PE foam core with high inner strength
- Suitable for automatic and manual module assembly
- Easy solar module assembly due to a high foam compression rate
- It consists of a highly conformable PE foam backing and a tackified acrylic adhesive.

Application Fields

- Solar module frames
- Mounting of trims and profiles
- General mounting applications

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-------------------|-------------------|-------------|
| • Backing | PE foam | • Total thickness | 800 µm |
| • Type of adhesive | tackified acrylic | • Color | black/white |

Properties/Performance Values

- | | | | |
|--------------------------|-----------|-------------------------------------|-------|
| • Elongation at break | 180 % | • Static shear resistance at 23°C | good |
| • Tensile strength | 12 N/cm | • Static shear resistance at 40°C | good |
| • Ageing resistance (UV) | very good | • Tack | good |
| • Humidity resistance | very good | • Temperature resistance long term | 80 °C |
| • Softener resistance | medium | • Temperature resistance short term | 80 °C |

tesa® 63608

Product Information

Adhesion to Values

• ABS (initial)	7.5 N/cm	• PET (after 14 days)	11 N/cm
• ABS (after 14 days)	11 N/cm	• PP (initial)	1.5 N/cm
• Aluminium (initial)	7 N/cm	• PP (covered side, after 14 days)	11 N/cm
• Aluminium (after 14 days)	11 N/cm	• PS (initial)	7.5 N/cm
• PC (initial)	7.5 N/cm	• PS (after 14 days)	11 N/cm
• PC (after 14 days)	11 N/cm	• PVC (initial)	5 N/cm
• PE (initial)	0.9 N/cm	• PVC (after 14 days)	11 N/cm
• PE (after 14 days)	1.2 N/cm	• Steel (initial)	11 N/cm
• PET (initial)	7.5 N/cm	• Steel (after 14 days)	11 N/cm

Additional Information

Liner variants:

- PV20 brown glassine paper /blue tesa logo
- PV50 transparent PET film
- PV15 blue PE film

Peel Adhesion:

- immediately: foam splitting on steel
- after 14 days: foam splitting on steel, ABS, Aluminium, PC, PET, PS, PVC

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=63608>